



General Purpose

Ortho phthalic type

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R135NNN	Non-Thixotropic Non - Promoted Non - wax resin	Clear, Slightly yellow	7 – 11	16 – 25	<ul style="list-style-type: none">- Well suited for hand lay up, spray up.- Septic tanks, general tanks.

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R235TPN	Thixotropic Promoted Non - wax resin	Cloudy reddish purple	20 - 45	2 – 5	<ul style="list-style-type: none">- Well suited for hand lay up, spray up.- Septic tanks, general tanks, cooling towers,- Boat, general FRP products.

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R235TPW	Thixotropic Promoted wax resin	Cloudy reddish purple	20 – 45	2 – 5	<ul style="list-style-type: none">- Well suited for hand lay up, spray up.- Septic tanks, general tanks, cooling towers,- Boat, general FRP products.

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R127TPN	Thixotropic Promoted Non - wax resin	Cloudy reddish purple	15 – 30	3 – 5	<ul style="list-style-type: none">- Well suited for hand lay up, spray up.- Septic tanks, general tanks, cooling towers,- Boat, general FRP products.



General Purpose

Ortho phthalic type

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R128NNN	Non -Thixotropic Non - Promoted Non - wax resin	Clear, Yellowish	5 – 8	4 – 8	- Well suited for hand lay up, spray up. - Septic tanks, general tanks, cooling towers,
Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR RF225TPN	Thixotropic Promoted Non - wax resin	Cloudy reddish purple	15 – 25	5 – 7	- Well suited for hand lay up, spray up. - Septic tanks, general tanks, cooling towers,
Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR C315	Non - Thixotropic Promoted Non - wax resin	Slightly reddish	20 – 40	13 – 17	- Well suited for artificial marble casting. - Usually casting compound is mixed 150 – 250 Phr filler as aluminium hydroxide, calcium carbonate.
Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R336HV	Thixotropic Non - Promoted Non - wax resin	Cloudy white	20 – 30	18 – 22	- Well suited for acrylic bath back up resin.



Excellent property of heat and hot water resistance

Iso phthalate type

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R289TPN	Thixotropic Promoted Non - wax resin	Cloudy reddish purple	20 – 45	3 – 5	Corrosion resistance tanks, duct, pipes and lining.
Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R295T	Non -Thixotropic Non - Promoted Non - wax resin	Clear, slightly yellow	10 – 25	3 – 7	Corrosion resistance tanks, duct, pipes and lining.



Excellent property of heat and hot water resistance

Bisphenol type

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR R2110	Thixotropic Non - Promoted Non - wax resin	Transparent	30 – 65	4 - 7	<ul style="list-style-type: none">- Corrosion resistance tanks, duct, pipes and lining.- This is a three pot resin, so when you apply this resin, it is necessary to add and mix- A. promoter like cobalt naphthenate- B.auxiliary accelerator like EP65- C. Catalyst like MEKPO

Vinyl ester type

Trade Name	Scope	Appearance	Gel time (minutes)	Viscosity (P)	Application and Properties
ESTAR H6650T	Thixotropic Non Promoted Non - wax resin	Yellowish Brown	20 – 40	-	<ul style="list-style-type: none">- Used for application in which process oxidation or alkali exposure includes.



Bulk Molding Compound based on Unsaturated polyester resin.

Prominate BM-ST610CT

Shrinkage	Gel Time (Sec.)	Cure Time (Sec.)	Spiral flow	Bacol Hardness	Bending modulus	Application
-0.03 - +0.09	15 – 23	19 – 30	200 – 400	45 – 65	12.7 – 14.7	- Prominate BM-ST610CT has been optimized for injection molding of headlamp reflector.